

## PREMABRAZE<sup>®</sup> 051

### ***NOMINAL COMPOSITION***

---

Gold	75.0% ± 0.5%
Copper	20.0% ± 0.5%
Silver	5.0% ± 0.5%
Other Volatile Elements (Each) <sup>(1)</sup>	0.002% Max
Volatile Elements Total (incl. Cd, Zn, Pb)	0.010% Max
Non-Volatile Elements (Total)	0.05% Max

<sup>(1)</sup> Elements with a vapor pressure higher than 10<sup>-7</sup> torr at 932°F (500°C) such as Mg, Sb, K, Li, Ti, S, Cs, Rb, Se, Te, Sr and Ca

### ***PHYSICAL PROPERTIES***

---

Color	Gold Red
Melting Point (Solidus)	1625°F (885°C)
Flow Point (Liquidus)	1643°F (895°C)
Brazing Temperature Range	1643°F - 1743°F (895°C - 951°C)
Specific Gravity	15.16
Density (Troy oz/in <sup>3</sup> )	7.99
Electrical Conductivity (%IACS) <sup>(2)</sup>	13.2
Electrical Resistivity (Microhm-cm)	13.1

<sup>(2)</sup> IACS = International Annealed Copper Standard

### ***PRODUCT USES***

---

Premabraz 051 can be used on any of the common ferrous and non-ferrous base alloys. Due to its low and narrow plastic range, this alloy is a preferred choice in step brazing operations. Premabraz 051 exhibits excellent vacuum properties along with high corrosion and oxidation resistance properties.

### ***BRAZING CHARACTERISTICS***

---

Premabraz 051 is a modified gold-copper alloy. It is generally used in reducing, vacuum, or inert atmosphere. It is a more ductile alloy than standard gold-copper alloys. The composition of the alloy allows for use in applications where braze filler metals low in volatile constituents are required.

### ***PROPERTIES OF BRAZED JOINTS***

---

The properties of a brazed joint are dependent upon the base metal, joint design and brazing technique. For controlled atmosphere brazing or vacuum brazing the recommended radial joint clearance for gold base alloys fall within 0.000 in. - 0.002 in. (0.00 mm - 0.05 mm.) range.

### ***AVAILABLE FORMS***

---

Wire, engineered preforms, specialty preforms per customer specification.

### ***SPECIFICATIONS***

---

Premabraz 051 alloy conforms to the following specifications: N/A

## ***APPLICABLE PRODUCT CODE(S)***

---

The applicable Lucas-Milhaupt product code(s) for this technical data sheet: A00000289, Legacy Code: 18-051.

## ***SAFETY INFORMATION***

---

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting". For more complete information refer to the Material Safety Data Sheet for Premabraz 051.

## ***WARRANTY CLAUSE***

---

Lucas-Milhaupt, Inc. believes the information contained herein to be reliable. However, the information is given by Lucas-Milhaupt, Inc. without charge and the user shall use such information at its own discretion and risk. This information is provided on an "AS IS" AND "AS AVAILABLE" basis and Lucas-Milhaupt, Inc. specifically disclaims warranties of any kind, either express or implied, including, but not limited to, warranties of title or implied warranties of merchantability or fitness for a particular purpose. No oral advice or written or electronically delivered information given by Lucas-Milhaupt, Inc. or any of its officers, directors, employees, or agents shall create any warranty. Lucas-Milhaupt, Inc. assumes no responsibility for results obtained or damages incurred from the use of such information in whole or in part.